



# gloveon

## Aegis

### Sterile Nitrile Exam Gloves Powder Free, Long Cuff

**Aegis**, like an armour, offers superb hand barrier protection and it dons like a second skin. The extended cuff length provides extra protection, high tensile strength and resistance to chemicals as expected from a high performance nitrile glove. This is our recommended sterile exam glove for procedures and jobs that demand tactile sensitivity.



GloveOn Aegis		
<b>Length (mm)</b>	≥ 280	
<b>Thickness Measurements (mm)</b>		
Palm (centre of Palm)	0.08 ± 0.02	
Finger (13mm ± 3mm from tip)	0.12 ± 0.02	
<b>Physical Properties</b>	<b>Before Ageing</b>	<b>After Ageing</b>
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 400
<b>Inspection Levels &amp; AQL</b>	<b>Inspection Level</b>	<b>AQL</b>
Watertightness	G1	1.50
Physical Dimensions	S2	4.00
Tensile Strength	S2	4.00
Visual Inspection (Major)	S4	2.50
Visual Inspection (Minor)	S4	4.00
Particulate Residue	N = 5	≤ 2mg/glove

#### REORDER CODE

SNT56SS	SMALL	(6.0 - 6.5)
SNT56MM	MEDIUM	(7.0 - 7.5)
SNT56LL	LARGE	(8.0 - 8.5)
SNT56XL	X-LARGE	(9.0)

#### FEATURES

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested
- Ambidextrous
- Long cuff
- Violet blue colour
- Sterilised using gamma irradiation

#### PACKAGING

1 pair per pouch  
50 pairs per box  
4 boxes per carton

#### REGULATORY COMPLIANCE

TGA - ARTG 203002, FDA 510(k),  
MDD 93/42/EEC, REACH,  
ROHS Directive 2002/95/EC

#### STANDARDS

ASTM D6319, EN455 part 1,2,3 & 4,  
ISO 11193-1, ISO 11137

#### MANUFACTURING ACCREDITATIONS

ISO 9001:2008  
ISO 13485:2003  
EN ISO 13485:2012

#### Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978-05-Test Report PN 104145A)

Minimum Breakthrough  
Detection Time (minutes)

Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	1.2 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Tospor), 20.0mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	30.9 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

**WARNING:** Carmustine and Thiotepa, at the tested concentration, degraded Aegis sterile nitrile glove at 1.2 minutes and 30.9 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

A brand by



**Mun Australia**  
Toll free: 1800 456 837 (GLOVES)  
info.au@munglobal.com



Protection Always On